

## PEREGRINE MATERIAL DECLARATION FORM

<b>Product:</b>	PE43503
<b>Ordering Codes:</b>	PE43503MLI, PE43503MLI-Z
<b>Description:</b>	50 Ohm RF Digital Attenuator 5-bit, 31 dB, 9 kHz - 6.0 GHz
<b>Package:</b>	24L 4X4 QFN
<b>Environmental Compliance</b>	EU RoHS Directive 2002/95/EC, <b>REACH</b> - EU ECHA SVHC, <b>Arsenic Free</b> , <b>JIG 101</b> - EIA/EICTA/JEITA, <b>Halogen Free</b> - IEC61249-2-21, <b>PFOS Free</b> - 2006/122/EC, <b>Antimony Trioxide Free</b>
<b>Lead Finish</b>	100% Matte Tin
<b>Availability</b>	Now

Component	Material	CAS Number	Weight (mg)	%	PPM
<b>Die</b>					
	Sapphire (Al <sub>2</sub> O <sub>3</sub> )	1344-28-1	2.020037	4.51%	45,056
	Silicon (Si)	7440-21-3	0.000670	0.00%	15
	Arsenic (As)	7440-38-2	0.000003	0.00%	0
	Boron (B)	7440-42-8	0.000001	0.00%	0
	Phosphorous (P)	7723-14-0	0.000226	0.00%	5
	Titanium (Ti)	7440-32-6	0.000077	0.00%	2
	Tungsten (W)	7440-33-7	0.000006	0.00%	0
	Copper (Cu)	7440-50-8	0.000010	0.00%	0
	Aluminum (Al)	7429-90-5	0.003363	0.01%	75
	Cobalt (Co)	7440-48-4	0.000000	0.00%	0
<b>Package</b>					
Leadframe	Copper (Cu)	7440-50-8	12.478300	27.83%	278,322
	Iron (Fe)	7439-89-6	0.300800	0.67%	6,709
	Zinc (Zn)	7440-66-6	0.015300	0.03%	341
	Phosphorus (P)	7723-14-0	0.003800	0.01%	85
	Silver (Ag)	7440-22-4	0.397800	0.89%	8,873
Die Attach	Silver (Ag)	7440-22-4	0.159100	0.35%	3,549
	Epoxy Resin	9003-36-5	0.039800	0.09%	888
	t-Butyl phenyl glycidyl ether	3101-60-8	0.016600	0.04%	370
	Phenolic hardener	92-88-6	0.003300	0.01%	74
	Butyl cellosolve acetate	112-07-2	0.002200	0.00%	49
Gold Wire	Gold (Au)	7440-57-5	0.032000	0.07%	714
100% Matte Tin Lead Finish	Tin (Sn)	7440-31-5	0.661100	1.47%	14,745
Mold Compound	Silica Fused	60676-86-0	26.317500	58.70%	586,997
	Epoxy Resin	Trade secret	1.148000	2.56%	25,606
	Phenol Resin	Trade secret	1.148000	2.56%	25,606
	Carbon Black	1333-86-4	0.086100	0.19%	1,920
<b>Total Weight (mg)</b>			<b>44.834094</b>	<b>100.00%</b>	<b>1,000,000</b>